# **GOLDSLIP EGN**

Antislipping to natural and synthetic fibers and their blends.

## **Fields of Application:**

• Finishing of cellulosic and synthetic fabrics and their blends by foulard.

#### **Characteristics:**

- Prevent slip fraying without changing the degree of white and / or color toner. Prevents fabric slipping without changing the degree of white and/or color shade.
- Compatible with other finishing products.
- Product has good stability if stored according to MSDS guidelines.
- This product complies with the parameters required by the OEKO-TEX<sup>®</sup> certification.
- This product fits within the requirements of the REACH regulation (Registration, Evaluation, Authorisation and Restriction of Chemicals, European Union).
- This product adapts the requirements of ZDHC program (Zero Discharge of Hazardous Chemicals).

### **Physicochemical parameters:**

Aspect	Colorless to translucent liquid.
Chemical Nature	Dispersion of colloidal silica.
ionic character	Nonionic.
Solubility (sol. 10% p/p)	Soluble at 25°C under stirring.
Nonvolatile content (%)	7.5 – 9.5
pH (Such as, 25°C)	9.5 – 10.5
Compatibility	Compatible with cationic, anionic or no ionic products, but it is recommended prior to test.

#### Application:

Foulard:	- 30.0 – 200.0 g/l of Goldslip EGN
	- Pick-up 50 - 100%

#### For data of security, ecological and toxicological, see the Safety Data Sheet (SDS).

Note: Given the variety of substrates and processes applications, the information here provided with fidelity, should be understood as a tool for guidance, therefore we cannot be responsible for any damages resulting from in inappropriate use. The data contained in this bulletin are based on current knowledge and current applications of our products performed. Additional information may be obtained from our technical department. Review: 09/27/2016.



R. Ambrosio Molina, 1090/1100 - Alameda 13 - Prédio D - CEP: 12247-902 - São José dos Campos - SP - Tel (12) 3908-5810